



Quality Paints since 1845
MATHYS®



FASSICRYL MATT

Water-based scratch-resistant matt lacquer

- Skin grease-resistant
- Scratch-resistance and easy to clean
- Excellent flow viscosity
- Good colour and gloss retention
- Easy to apply with a brush and a roller



FASSICRYL MATT

DESCRIPTION

Fassicryl Matt is a top-quality water-based matt indoor lacquer based on PU acrylate. Suitable as a top layer to cover wood as well as any pre-treated surface such as plastic or metal. Fassicryl Matt is scratch-resistant and skin grease-resistant. The paint has excellent flow viscosity and good colour and gloss retention.

RECOMMENDED USE

This water-based scratch-free matt lacquer is suitable as a top layer to cover wood as well as any properly pre-treated surface such as plastic or metal.

RECOMMENDED SYSTEM

Priming with Fassicryl Primer. Use Fassicryl Sealing Primer on bleeding wood types. Finish with a Fassicryl lacquer.

TECHNICAL DATA

Density (g/cm ³):	1,23 (white - wit - blanc - weiß)
Gloss Level:	Matt
Gloss level at 60°:	5-10%
Solids content in volume:	37% (white - wit - blanc - weiß)

DRY TIMES BY 20° C/RV 50%

Touch dry:	1 hour
Dry to recoat:	6 hours

RECOMMENDED WET FILM THICKNESS

67 µm (white - wit - blanc - weiß)

RECOMMENDED DRY FILM THICKNESS

25 µm (white - wit - blanc - weiß)

THEORETICAL CONSUMPTION

15 m²/l/coat

PRACTICAL CONSUMPTION

Practical coverage depends on many factors such as porosity and roughness of the substrate and material losses during application.

SURFACE PREPARATION

The surface must be dry and free of dust and grease. Round off sharp edges so that you can apply a good coating.

New work: priming with Fassicryl Primer. Use Fassicryl Sealing Primer on bleeding wood types.

Existing work: lightly sand old and properly adhesive coats. Remove loose, cracked or flaky coats. Treat exposed locations as new wood.

DIRECTIONS FOR USE

To ensure homogeneity, thoroughly stir prior to use.

APPLICATION CONDITIONS

> 8°C, < 80% R.H.

APPLICATION & THINNING: BRUSH

Apply undiluted with brush with synthetic bristles.

APPLICATION & THINNING: ROLLER

Apply undiluted with a 10 mm micro fiber roller.

CLEANING OF EQUIPMENT / SPILLS

Clean the material with water and dispose of the residue appropriately.

REMARKS

Do not apply paint at temperatures below 8°C. The surface temperature must be at least 3°C above the dew point.

Scratch-resistance is achieved after 15-30 days depending on the colour.

SAFETY DATA

VOC level:	40g/l
VOC ready mix:	40g/l
VOC category:	IIA/d
VOC limit:	130g/l
Remarks regarding safety:	Consult Safety Data Sheet and Safety Information printed on the can.

SHELF LIFE

Minimum of 2 years from date of production in unopened cans, if stored in dry, well ventilated areas, not in direct sunlight at temperatures between 5 and 35°C.

Date issued: 19/10/2022

Available colours & pack sizes: Please refer to the respective product page on www.rust-oleum.eu for an overview of actual available colours and pack sizes.

Disclaimer: The information contained herein is to the best of our knowledge true and accurate and is given in good faith but without warranty. The user will be deemed to have satisfied him/herself independently as to the suitability of our products for his/her own particular purpose. In no event shall Rust-Oleum Europe be liable for consequential or incidental damages. Products must be stored, handled, and applied under conditions complying with Rust-Oleum Europe recommendations detailed within the latest copy of the product data sheet. It is the user's responsibility to ensure that they have the current copy. Latest copies of the product data sheet is available for free and downloadable from www.rust-oleum.eu or upon a request to our Customer Services department. Rust-Oleum Europe reserves the right to change the properties of its' products without prior notification.

Rust-Oleum Netherlands B.V.
Zilverenberg 16
5234 GM 's-Hertogenbosch
The Netherlands
T : +31 (0) 165 593 636
F : +31 (0) 165 593 600
info@rust-oleum.eu

Tor Coatings Ltd (Rust-Oleum Industrial)
Shadon Way, Portobello Ind. Estate
Birtley, Chester-le-Street
DH3 2RE United Kingdom
T : +44 (0)1914 113 146
F : +44 (0)1914 113 147
info@rust-oleum.eu

Rust-Oleum France S.A.S.
38, av. du Gros Chêne
95322 Herblay
France
T : +33(0) 130 40 00 44
F : +33(0) 130 40 99 80
info@rust-oleum.eu

N.V. Martin Mathys S.A.
Kolenbergstraat 23
3545 Zelem
Belgium
T : +32 (0) 13 460 200
F : +32 (0) 13 460 201
info@rust-oleum.eu